Series 206

INTERIOR EGGSHELL ENAMEL

Manufacturer of Paints and Stains
www.fmipaint.com

PRODUCT DESCRIPTION:

"SERIES 206 INTERIOR EGGSHELL ENAMEL" IS A SELF-PRIMING INTERIOR EGGSHELL ENAMEL SUITABLE FOR MODERATE TRAFFIC AREAS. THIS LOW LUSTER RESISTS DIRT AND GRIME AND PROVIDES THE ULTIMATE IN DURABILITY AND HIDING. SERIES 206 PRODUCES A SOFT VELVETY APPEARANCE.

RECOMMENDED USES:

"SERIES 206 INTERIOR EGGSHELL ENAMEL" IS RECOMMENDED FOR MODERATE TRAFFIC AREAS SUCH AS FAMILY ROOMS, LIVING ROOMS, DINING ROOMS, BEDROOMS AND HALLWAYS. RECOMMENDED FOR SHEETROCK OR PLASTER WALLS AND WOOD TRIM.

PERFORMANCE INFORMATION:

PRIMER AND FINISH IN ONE. BEAUTIFUL LOW ANGULAR SHEEN. CAN BE APPLIED BY A BRUSH, ROLLER OR SPRAY. MILDEW RESISTANT. HIGH HIDING.

APPLICATION AND REDUCTION INFORMATION:

THIS PRODUCT HAS BEEN DESIGNED FOR BRUSH, ROLL, PAD OR SPRAY APPLICATION. THINNING IS NOT RECOMMENDED. APPLY AT TEMPERATURES ABOVE 50F. PROTECT FROM FREEZING.

CHARACTERISTICS:

VEHICLE: ACRYLIC
FINISH: EGGSHELL/SOFT GLOSS
SPREAD RATE: 250-400 SF/GAL DEPENDING ON VERACITY.
DRYING TIME: DRIES TO TOUCH IN 1 HOUR. TO RE-COAT, 4 HOURS.
WEIGHT: 11.7 LBS PER GAL.
PERCENT SOLIDS/VOLUME: 39.8% + OR – 2
PERCENT SOLIDS/WEIGHT: 56.96% + OR – 2
VISCOSITY: 95-110 KU'S
PACKAGING: 5 GAL. CONTAINER, 2 GAL. CONTAINERS
VOC'S: .68 LBS./.GAL.

CLEAN-UP INFORMATION:

CLEAN UP EQUIPMENT AND AREA WITH DETERGENT AND WATER. FLUSH SPRAY EQUIPMENT WITH MINERAL SPIRITS AFTER CLEANING WITH WATER OR DETERGENT AND WATER.

SPECIFICATION

SURFACE PREPARATION:

ALL SURFACES SHOULD BE PROPERLY PREPARED AND CLEANED. LOOSE PAINT SHOULD BE SCRAPED AND SANDED TO A SMOOTH SURFACE. WASH OFF DIRT AND GREASE WITH HOUSEHOLD DETERGENT, RINSE AND ALLOW TO DRY. LIGHTLY SAND GLOSSY SURFACES TO A DULL FINISH. FILL ANY CRACKS OR HOLES WITH THE APPROPRIATE FILLER, ALLOW TO DRY AND SAND TO A SMOOTH SURFACE. REMOVE ALL DUST WITH A DAMP CLOTH. ALL NEW STUCCO, PLASTER AND MASONRY MUST BE ALLOWED TO CURE FOR 30 DAYS PRIOR TO PAINTING.

PRIMING:

SERIES 206 INTERIOR EGGSHELL ENAMEL IS SELF-PRIMING. SPECIAL PRIMERS ARE NOT NECESSARY OVER PROPERLY PREPARED UNCOATED AND PREVIOUSLY PAINTED INTERIOR SURFACES. WATER STAINS, SMOKE, INK, KNOTS AND ANY OTHER STAINS THAT HAVE THE POTENTIAL TO BLEED THROUGH SHOULD BE PRIMED WITH AN APPROPRIATE STAIN BLOCKING PRIMER.

MILDEW:

IF IT IS DETERMINED THAT THE SURFACES ARE CONTAMINATED WITH SPORES, MILDEW, FUNGUS, ETC., REMOVE BY SCRUBBING OR POWER WASHING SURFACE WITH A SOLUTION OF 1 CUP HEAVY DUTY, ABRASIVE CLEANER AND 1 QUART HOUSEHOLD BLEACH DISSOLVED INTO 3 QUARTS WATER. APPLY LIBERALLY TO ALL AFFECTED SURFACES. ALLOW SOLUTION TO REMAIN ON SURFACE UNTIL THERE IS VISIBLE ALTERATION TO BIOLOGICAL CONTAMINANTS. DARK SPOTS SHOULD DISAPPEAR. FLUSH SURFACE THOROUGHLY WITH WATER, ALLOW TO DRY COMPLETELY, AND THEN APPLY "INTERIOR EGGSHELL ENAMEL."

DISCLAIMER

The information in this data sheet is given to the best of FMI Paint's knowledge and practical experience. Users may consult with FMI Paint on the general suitability of the product for their needs and specific application practices though it remains each user's responsibility to determine the suitability of the product for the user's particular use. The condition of the substrate and application are not within FMI Paint's control. Therefore no implied conditions, warranties or other terms will apply to the Product. FMI Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will FMI Paint be liable to the user for any kind of loss (whether direct or indirect) even if FMI Paint was previously advised of it. In line with FMI Paint's policy for continuous development and improvement, FMI Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user's responsibility to check with FMI Paint for the latest version of this data sheet.