Series 404

"PEERLESS" 100% ACRYLIC LINE MARKING PAINT

Manufacturer of Paints and Stains
www.fmipaint.com

PRODUCT DESCRIPTION:

"PEERLESS" LINE MARKING PAINT IS A 100% WATERBORNE ACRYLIC PAINT DEVELOPED TO CONFORM WITH FEDERAL SPECIFICATION TT-P-1952F Type I & II. RECOMMENDED FOR MARKING PARKING LOTS, CURBS, AND WAREHOUSE FLOORS. USE ON ASPHALT, CONCRETE, BRICK AND STONE.

ADVANTAGES

- EXCELLENT ADHESION
- NON-FADING
- EXCELLENT DURABILITY
- SOAP & WATER CLEANUP
- SNAP DRYING
- NO BLEED THROUGH
- NO FOGGING
- HIGH HIDING
- MINIMAL FILTERING REQUIRED

SURFACE PREPERATION:

REMOVE ALL SURFACE CONTAMINATION BY WASHING WITH AN APPROPRIATE CLEANER, RINSE THOROUGHLY AND ALLOW COMPLETE DRYING. EXISTING PEELED OR CHECKED PAINT SHOULD BE SCRAPED AND SANDED TO A SOUND SURFACE. GLOSSY SURFACES SHOULD BE SANDED DULL OR SCRUBBED WITH AN ABRASIVE CLEANER. SURFACE SHOULD BE CLEAN AND DRY AND FREE FROM LOOSE OR PEELING PAINT. THE PRESENCE OF CONCRETE SEALERS OR EFFLORESCENCE ON NEW CONCRETE MAY INTERFERE WITH ADHESION AND SHOULD BE REMOVED. MOST PREVIOUSLY PAINTED LINES MAY BE REPAINTED WITHOUT ADDITIONAL SURFACE PREPARATION, PROVIDED THE OLD PAINT IS STILL TIGHTLY ADHERED TO THE SURFACE. NEW ASPHALT SURFACES SHOULD IDEALLY BE ALLOWED TO AGE SEVERAL MONTHS BEFORE STRIPING.

CHARACTERISTICS:

VEHICLE: 100% ACRYLIC.
FINISH: MATTE
DRYING TIME: DRIES TO TOUCH IN 5 MIN. TO RE-COAT, 1 HOUR.
WEIGHT: 14 LBS. PER GAL.
PERCENT SOLIDS/VOLUME: 60.8
PERCENT SOLIDS/WEIGHT: 77.8
VISCOSITY: 90-95 KU'S
RECOMMENDED FILM THICKNESS: 12 MILS WET; 7.9 MILS DRY
PACKAGING: 5 GAL. CONTAINER
VOC'S: 65 GRAMS PER LITER, LESS WATER

APPLICATION AND REDUCTION INFORMATION:

DO NOT PAINT ON WET SURFACES OR WHEN HUMIDITY IS ABOVE 85% OR WHEN AIR OR SURFACE TEMPERATURES MAY FALL BELOW 35 DEG. F WITHIN 4 HOURS OF APPLICATIONS. A LINE MARKING SPRAY MACHINE IS RECOMMENDED AND THINNING IS NOT RECOMMENDED. APPLY @12 WET MILS, 7.3 DRY. IF NECESSARY, THIN WITH UP TO 1 PINT PER GALLON OF WATER. USE .015" - .017" TIP, 50 – 100 MICRON FILTER AND 1,800 TO 2,700 PSI FLUID PRESSURE. IF ROLLING USE APPROPRIATE SIZE ROLLER FOR DESIRED LINE WIDTH. NO THINNING IS NECESSARY. USE APPROPRIATE SYNTHETIC 3/8"-3/4" NAP SIZE ROLLER COVER. CLEAN UP: WET PAINT MAY BE CLEANED UP WITH WARM SOAPY WATER. ONCE THE PAINT IS DRY, A SOLVENT (E.G. XYLENE, TOLUENE, ETC.) MAY BE NECESSARY TO DISSOLVE DRIED PAINT.

CLEAN-UP INFORMATION:

CLEAN UP IMMEDIATELY WITH WARM SOAP AND WATER. FLUSH EQUIPMENT WITH COPIOUS AMOUNTS OF WATER TO COMPLETELY CLEAN ALL LINES AND EQUIPMENT.

DISCLAIMER

The information in this data sheet is given to the best of FMI Paint's knowledge and practical experience. Users may consult with FMI Paint on the general suitability of the product for their needs and specific application practices though it remains each user's responsibility to determine the suitability of the product for the user's particular use. The condition of the substrate and application are not within FMI Paint's control. Therefore no implied conditions, warranties or other terms will apply to the Product. FMI Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will FMI Paint be liable to the user for any kind of loss (whether direct or indirect) even if FMI Paint was previously advised of it. In line with FMI Paint's policy for continuous development and improvement, FMI Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user's responsibility to check with FMI Paint for the latest version of this data sheet.